St. John Fisher University

Fisher Digital Publications

Pharmacy Faculty/Staff Publications

Wegmans School of Pharmacy

11-2016

Influence of key polymer attributes, manufacturing conditions and sintering on abuse deterrence of physical barrier type abuse deterrent formulations (ADF)

Heather Boyce

University of Maryland - Baltimore

Vivek S. Dave

St. John Fisher University, vdave@sjf.edu

Myke Scoggins

Micromeritics

Dan Smith

Purdue University

Follow this and additional works at: https://fisherpub.sjf.edu/pharmacy_facpub

Steve Byrn

Part of the [Pharmacy and Pharmaceutical Sciences Commons](#)

How has open access to Fisher Digital Publications benefited you?

see next page for additional authors

Publication Information

Boyce, Heather; Dave, Vivek S.; Scoggins, Myke; Smith, Dan; Byrn, Steve; Saluja, Bhawana; Qu, Wen; Gurvich, Vadim J.; and Hoag, Stephen W., "Influence of key polymer attributes, manufacturing conditions and sintering on abuse deterrence of physical barrier type abuse deterrent formulations (ADF)" (2016). *Pharmacy Faculty/Staff Publications*. Paper 416.

https://fisherpub.sjf.edu/pharmacy_facpub/416

Please note that the Publication Information provides general citation information and may not be appropriate for your discipline. To receive help in creating a citation based on your discipline, please visit <http://libguides.sjfc.edu/citations>.

This document is posted at https://fisherpub.sjf.edu/pharmacy_facpub/416 and is brought to you for free and open access by Fisher Digital Publications at . For more information, please contact fisherpub@sjf.edu.

Influence of key polymer attributes, manufacturing conditions and sintering on abuse deterrence of physical barrier type abuse deterrent formulations (ADF)

Abstract

When sintering is used to treat tablet formulations containing polyethylene oxide (PEO), the polymer particles are able to form stronger bonds thereby increase tablet tensile strength. This increase in strength can make it more difficult for an abuser to break, chew, or grind opioid tablets. A mechanistic study was implemented to understand the key sintering factors that influence tensile strength.

Disciplines

Pharmacy and Pharmaceutical Sciences

Comments

Poster presented at the American Association of Pharmaceutical Scientists (AAPS) Annual Meeting and Exposition in Denver, Colorado, November 2016.

Authors

Heather Boyce, Vivek S. Dave, Myke Scoggins, Dan Smith, Steve Byrn, Bhawana Saluja, Wen Qu, Vadim J. Gurvich, and Stephen W. Hoag

31T0400 Influence of key polymer attributes, manufacturing conditions and sintering on abuse deterrence of physical barrier type abuse deterrent formulations (ADF)

Heather Boyce¹, Vivek Dave², Myke Scoggins³, Dan Smith⁴, Steve Byrn⁴, Bhawana Saluja⁵, Wen Qu⁶, Vadim J. Gurvich⁷, Stephen W. Hoag¹

1. University Maryland Baltimore, School of Pharmacy | 2. St John Fischer, Wegmans School of Pharmacy | 3. Micromeritics | 4. Purdue University
5. Office of Clinical Pharmacology, U.S. Food and Drug Administration | 6. Office of Pharmaceutical Quality, U.S. Food and Drug Administration | 7. NIPTE

Purpose

When sintering is used to treat tablet formulations containing polyethylene oxide (PEO), the polymer particles are able to form stronger bonds thereby increase tablet tensile strength. This increase in strength can make it more difficult for an abuser to break, chew, or grind opioid tablets. A mechanistic study was implemented to understand the key sintering factors that influence tensile strength.

Methods

The ADF tablets were composed of PEO and inert filler dicalcium phosphate anhydrous. 10 mm flat faced tooling was used to compress the tablets on a Beta Manesty press.

Sintering Variables

- Tablet solid fraction (SF)
[0.73, and 0.8] [0.77 used for SF PEO]
- PEO particle size
[superfine & standard]
- standard size PEO taken directly from the container or SF PEO obtained from the sieve fraction of 150 to 250 μm was used.
- sintering time @ 80°C
[0, 0.167, 0.5, 1, 3, 9 and 15 hr]
- Concentration of PEO
[30, 50, 70 wt%]

Tablet Characterization Techniques

- SEM
- DSC (crystallinity)
- Pore diameter by Mercury porosimetry
- BET surface area
- Hardness Tester for tensile strength

Results

Tablet Microstructure Characterization

Significant tablet microstructural changes occur within the first 1 hr of sintering

- Decrease in surface area
- Increase in pore diameter
- Decrease in PEO crystallinity

A rapid decrease in surface area within the first 10 minutes demonstrates the sintered particles' grain boundary grows rapidly (coarsening). Coarsening continues at later time points but it is not significant enough to impact microstructure or resulting strength. Pore diameter increases align with the observation that PEO rapidly coarsens under the study conditions. Mercury porosimetry shows that the degree of pore diameter coarsening is controlled by the initial solid fraction and the percentage of PEO in the dosage form. When all 30% PEO is present, there is no coarsening and therefore the tensile strength increases are minimal for the 30% PEO tablets. As the tablets are sintered the crystallinity of PEO decreases. The subsequent increase in PEO amorphicity increases the PEO ductility and therefore the overall strength of the dosage form.

Properties of PEO that lead to abuse deterrence

- Low Glass Transition: -70°C
- Linear backbone structure for highly ordered crystal structure
- Highly crystallinity >90% provides overall strength
- Amorphous components allow for toughness or exhibits ductile behavior

Tensile Strength: Abuse Deterrent Response

Tensile strength impacted by

- Fractional density at low PEO content (high m value)
- A smaller particle size distribution (SF PEO)
- High initial solid fraction

As the amount of PEO in the dosage form increases, the tensile strength becomes less dependent on solid fraction of the dosage form as indicated by high m values. The sintering time was found not to significantly increase the tensile strength after 1 hr of sintering. Significant tensile strength gains were only realized during first 1 hr of sintering in which significant tablet microstructure changes occurred. Finally, the super fine PEO demonstrated a huge increase in tensile strength in the non-sintered state. The sintered tablets made with superfine PEO were unable to be broken under compressive stress and 300 N.

Tensile Strength (N/cm²)	
Unsintered 70% PEO	
Super fine	56 ± 7
0.8 SF standard	31 ± 2
0.73 SF standard	14 ± 1

Fit Parameters	70% PEO	50% PEO	30% PEO
m	8	10	15
R²	0.84	0.79	0.99

Conclusions

- When sintering PEO with dicalcium phosphate anhydrous at 80°C, the microstructural changes occur within 1 hour of sintering.
- The tensile strength increases only when the microstructure is changing; sintering between 1 to 15 hr does not yield any significant increases in tensile strength.
- The decrease in crystallinity results in more amorphous regions in the PEO lattice which could increase the ductility of the dosage form.
- A high initial solid fraction yields a more controlled sintering process.

References

- German RM. Sintering Theory and Practice. New York, NY: John Wiley and Sons, Inc.; 1996.
- McKenna WH, Mannion RO, O'Donnell EP, Huag HH, inventors; Purdue Pharma L.P., assignee. Tamper Resistant Dosage Forms. United States patent 8808741. 2014
- German RM. Surface area reduction during isothermal sintering. Journal of American Ceramic Society. 1976;59(9/10):379-83

Acknowledgements

We are grateful to the National Institute for Pharmaceutical Technology and Education (NIPTE) and the U.S. Food and Drug Administration (FDA) for providing funds for this research. This study was funded by the FDA contract to NIPTE # HHSF223201301189P. We would also like to thank Micromeritics Instrument Company for the generous donation of analytical services to conduct the mercury porosimetry and surface area measurements. We would also like to thank DOW chemical for their generous donation of POLYOX.

UNIVERSITY of MARYLAND
SCHOOL OF PHARMACY